



LC – ALUMINA TRIHYDRATE – DRY

Sales Specification

<u>Chemical Property</u>	<u>Typical</u>	<u>Sales Specification</u>
* Al ₂ O ₃ , wt/wt %	64.5 – 65.0	64.0 – 65.5
* CaO, wt/wt %	0.007	0.13 max
* SiO ₂ , wt/wt %	0.007 – 0.012	0.015 max
* Fe ₂ O ₃ , wt/wt %	0.008 – 0.013	0.02 max
* Na ₂ O, wt/wt %	0.24 – 0.30	0.4 max
* TiO ₂ , by wt/wt %	0.002 – 0.003	0.01 max
* Acid Insoluble, wt/wt %	0.03 – 0.09	0.15 max
* Free Moisture, wt % @ 105°C	0.08 – 0.10	0.2 max

Physical Property

Loose Bulk Density, lb/ft ³	75 – 85	
Particle Size, cumulative		
* +100 mesh, %	10 – 20	20 max
* +200 mesh, %	69 – 83	60 min
* +325 mesh, %	92 – 97	88 min
* - 325 mesh, %	< 5	12 max

*Certificate of Analysis Properties

LC – Alumina Trihydrate – Dry is a coarse, off-white, hydrated alumina.

Southern Ionics may accommodate other customer needs upon request.

For information on safety and handling, consult the Safety Data Sheet (SDS) for Alumina Trihydrate – Dry available at www.southernionics.com or by contacting Southern Ionics Customer Service at 1-800-953-3585.



P.O. Box 1217
579 Commerce Street
West Point, MS 39773

To Place an Order or For Inquiries:
Tel: 800-953-3585 / Fax: 800-953-3588
Email: sii_custserv@southernionics.com

Website: www.southernionics.com

Notice: No freedom from any patent or other intellectual property rights owned by SII or others is to be inferred. SII assumes no obligation or liability for the information in this document. The information provided herein is presented in good faith and is based on the best of SII's knowledge, information, and belief. Since use and conditions of use at non-SII facilities are beyond SII's control, and government requirements may differ from one location to another and may change with time, it is solely the Buyer's responsibility to determine whether SII's products are appropriate for the Buyer's use and to assure the Buyer's workplace, use, and disposal practices are in compliance with applicable government requirements. Consequently, SII assumes no obligation or liability for use of these materials and makes no warranty, express or implied. Buyer's use of the information provided herein is solely the Buyer's responsibility for compliance with any applicable government requirements. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.