

GR – ALUMINA TRIHYDRATE – WET

Sales Specification

	<u>Chemical Property</u> <u>dry basis – unless noted</u>	<u>Typical</u>	Sales Specification
*	Al ₂ O ₃ , wt/wt %	65.25	64 min
*	SiO ₂ , wt/wt %	0.005	0.015 max
*	Fe ₂ O ₃ , wt/wt %	0.006	0.020 max
*	Na ₂ O, wt/wt %	0.22	0.460 max
*	TiO ₂ , by wt/wt %	0.0004	0.005 max
*	Acid Insoluble, wt/wt %	0.02	0.80 max
*	Free Moisture, wt % (105°C, neat basis)	7.05	12.50 max
	CaO, by wt/wt %	0.027	
	Caustic Insoluble, wt/wt %		0.20 max
	Leachable Na ₂ O	0.009	
	Physical Property		
	Loose Bulk Density, lb/ft ³ Particle Size, cumulative	55 – 65	
	* + 100 mesh, %	5.4	20 max
	* + 325 mesh, %	93	
	*Oputificate of Analysis Duomontins		

^{*}Certificate of Analysis Properties

GR – Alumina Trihydrate – Wet is a coarse, off-white, hydrated alumina.

Southern Ionics may accommodate other customer needs upon request.

For information on safety and handling, consult the Safety Data Sheet (SDS) for Alumina Trihydrate – Wet available at www.southernionics.com or by contacting Southern Ionics Customer Service at 1-800-953-3585.



P.O. Box 1217 579 Commerce Street West Point, MS 39773

To Place an Order or For Inquiries: Tel: 800-953-3585 / Fax: 800-953-3588 Email: sii custserv@southernionics.com

Website: www.southernionics.com

Notice: No freedom from any patent or other intellectual property rights owned by SII or others is to be inferred. SII assumes no obligation or liability for the information in this document. The information provided herein is presented in good faith and is based on the best of SII's knowledge, information, and belief. Since use and conditions of use at non-SII facilities are beyond SII's control, and government requirements may differ from one location to another and may change with time, it is solely the Buyer's responsibility to determine whether SII's products are appropriate for the Buyer's use and to assure the Buyer's workplace, use, and disposal practices are in compliance with applicable government requirements. Consequently, SII assumes no obligation or liability for use of these materials and makes no warranty, express or implied. Buyer's use of the information provided herein is solely the Buyer's responsibility for compliance with any applicable government requirements. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.